

## Product Data Sheet – Struc-Dash – Dash Receiver

Structherm Dash Receivers are cement based, polymer modified and self-coloured, requiring only the addition of water and 10 minutes mixing time. Normally applied as an excellent background for any dry dash or roughcast finish for new build or refurbishment. All Structherm Dash Receivers are ISO 9001 approved and are Kitemarked to BE EN 998-1.

### STANDARD DASH

For general use, normally applied on to Structherm Base Coats.  
Apply 6-8mm thick, depending on the size of the dashing aggregate.

Coverage: 1.5kg per mm thick per sq m.  
Required: 10 – 12kg per sq meter approx..  
Nominal: 6-8mm thickness  
Water required: 5-6L/bag

### SILICONE DASH

Silicone Dash is specifically designed to incorporate the benefits of silicone water repellents into a cement-based render system. Silicone adds a high-water repellent quality, while allowing water vapour to pass freely through the render; thus the amount of dirt adhering to the surface is greatly reduced, ensuring a freshly rendered appearance for a prolonged period of time. This dry surface also improves the resistance of the finished render to algae growth and the natural phenomenon of lime-bloom.

Coverage: 1.5kg per mm thick per sq m.  
Required: 10 – 12kg per sq meter approx..  
Nominal: 6-8mm thickness  
Water required: 5-6L/bag

### OVERCOATING SILICONE DASH

Overcoating Silicone Dash is specifically designed for refurbishment over existing dry dash finishes. Apply 6 - 8mm thick.

Coverage: 1.0kg per mm thick per sq m.  
Required: 8 – 12kg per sq meter approx..  
Nominal: 6-8mm thickness  
Water required: 4.5-5.5L/bag

### SILICONE SPRAY DASH

A silicone enhanced Dash Receiver which may be spray applied, normally on to K Rend Base Coats. Apply 6 - 10mm thick, depending on the size of the dashing aggregate.

Coverage: 1.5kg per mm thick per sq m.  
Required: 10 - 15kg per sq metre approx..  
Nominal: 6 - 8mm thickness  
Water required: 4.5 - 5.5L / bag

### HIGH POLYMER DASH RECEIVER

This polymer-modified render is normally applied to High Polymer Base Coat as part of a thin coat render system. Apply 6 - 8mm thick, depending on the size of the dashing aggregate.

Coverage: 1.5kg per mm thick per sq m  
Required: 10 - 12kg per sq metre approx.  
Water required: 5-6L / bag

**APPLICATION**

Mix thoroughly for at least 10 minutes to break down additives.  
Add appropriate quantity of clean water per 25kg sack.  
Apply a butter coat of render to a uniform thickness, depending on the aggregate size.  
While the render is still plastic, throw washed aggregate onto the surface to give a uniform dense coverage.  
Immediately tamp the aggregate particles lightly into the butter coat with a wood float and ensure a good bond is obtained.

**STRUCTHERM RENDERS**

There are many benefits to be gained from using K Rend renders:

- Low maintenance
- Water resistant and extremely durable
- Wide range of attractive colours
- Suitable for different substrates

**PACKAGING**

K Rend renders are usually packed 40 sacks per tonne, loaded 70 per 1.75 tonne pallet.

All render sacks must be protected on site.

Shelf life is approximately one year in dry conditions in original packaging.

It is important to note that all Structherm renders are non- returnable.

**TECHNICAL ADVICE**

For use of these products, please seek technical advice by contacting your sales representative

---